

OFFICE OF NAVAL RESEARCH

Contract N00014-92J-1810


R&T CODE: 4133030

TECHNICAL REPORT NO. 11

Characterization and Electrochemical Properties  
of Electrosynthesized Carbonaceous Fibers

by

Michael J. Shane, Beatrice K. Chinh, and Michael J. Sailor



Prepared for publication

in

*Extended Abstracts*  
The 188th Electrochemical Society Meeting  
Chicago, Illinois  
October 8-13, 1995

Department of Chemistry and Biochemistry  
University of California, San Diego  
9500 Gilman Drive, Dept 0358  
La Jolla, CA 92093-0358

August 1, 1995

Reproduction in whole or in part is permitted for  
any purpose of the United States Government

This document has been approved for public release  
and sale; its distribution is unlimited

DTIC QUALITY INSPECTED 5

19950816 097

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE August 1, 1995	3. REPORT TYPE AND DATES COVERED Interim	
4. TITLE AND SUBTITLE Characterization and Electrochemical Properties of Electrosynthesized Carbonaceous Fibers		5. FUNDING NUMBERS Contract # N00014-92J-1810	
6. AUTHOR(S) Michael J. Shane, Beatrice K. Chinh, and Michael J. Sailor			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Dr. Michael J. Sailor Department of Chemistry and Biochemistry University of California, San Diego La Jolla, CA 92093-0358		8. PERFORMING ORGANIZATION REPORT NUMBER  ONR TECHNICAL REPORT #11	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 800 North Quincy Street Arlington, VA 22217		10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES			
12a. DISTRIBUTION/AVAILABILITY STATEMENT Reproduction in whole or in part is permitted for any purpose of the United States Government. This document has been approved for public release and sale; its distribution is unlimited.		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Carbonaceous fibers with diameters ranging from 0.1-5 microns and lengths up to several hundred microns spontaneously form during cathodic electrodecomposition of $\text{CCl}_4$ in nonaqueous solvents ( $\text{CH}_3\text{CN}$ or $\text{CH}_2\text{Cl}_2$ ) containing tetrabutylammonium salts. The fiber morphology is dependent on current density, $\text{CCl}_4$ concentration, and electrode surface preparation. X-ray photoelectron spectroscopic measurements revealed that the fibers consist primarily of carbon, with some nitrogen, chlorine, and oxygen impurities. X-ray and electron diffraction showed the fibers to be amorphous.			
14. SUBJECT TERMS electrodeposition, carbon, fibers		15. NUMBER OF PAGES	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT


# Characterization and Electrochemical Properties of Electrosynthesized Carbonaceous Fibers

Michael J. Shane, Beatrice K. Chinh, and  
Michael J. Sailor  
Department of Chemistry and Biochemistry  
University of California at San Diego  
9500 Gilman Drive, La Jolla, CA 92093-0358

## Introduction

Carbon fibers and films are useful materials for several different electrochemical applications, including stable electrodes for electrochemical synthesis and battery applications.<sup>1</sup> Carbon materials are usually deposited by physical methods such as sputtering, or the decomposition of hydrocarbons at high temperatures. Carbon films have also been formed electrochemically, either by reduction of halogenated hydrocarbons<sup>2-4</sup> or reduction of fluorinated polymers.<sup>5</sup>

We have recently discovered a method by which carbonaceous materials are deposited in the form of small fibers, which due to their unusual morphology may have applications in several fields. The deposition proceeds through the reduction of carbon tetrachloride in an organic solvent. The net reaction can be written as:



Carbon fibers are formed at the cathode as a result of this reaction. The fibers have diameters from 0.1-5  $\mu\text{m}$ , and lengths up to several hundred microns. The fibers have been grown on Ni, Cu, Ag, Pt, or Fe substrates, with the morphology being dependent on current density,  $\text{CCl}_4$  concentration, and electrode surface preparation.

## Preparation

Working electrodes with areas of approximately 0.25  $\text{cm}^2$  were cut from 99.5% purity metal foils (Johnson Matthey Electronics, Aldrich Chemicals). The electrodes were polished with 1  $\mu\text{m}$  alumina or 85  $\mu\text{m}$  SiC. Solvents were distilled under nitrogen from the appropriate drying agent, and  $\text{CCl}_4$  was vacuum distilled before use.<sup>6</sup> The electrolytic deposition solutions typically consisted of 30 mL of solvent ( $\text{CH}_3\text{CN}$  or  $\text{CH}_2\text{Cl}_2$ ), 1 mL of  $\text{CCl}_4$ , and 1.5g of tetrabutylammonium tetrafluoroborate (TBABF<sub>4</sub>) or 1.3g of bis-(triphenylphosphoranylidene) ammonium chloride (PPNCl) (Aldrich Chemicals). All electrodeposition experiments were carried out in a two-compartment cell under either argon or nitrogen atmospheres. The platinum counter electrode was separated from the working and reference electrodes by a glass frit. The applied current density was typically 3-5  $\text{mA/cm}^2$  and the galvanostatic depositions were carried out for 30-60 min.

## Results

Figure 1 shows an electron micrograph of fibers formed on a copper substrate from a solution of  $\text{CH}_3\text{CN}$  and

TBABF<sub>4</sub>. The fibers are approximately 0.1-5 microns in diameter and range in length up to 200 microns. The size and density of fibers is dependent on electrode preparation, with coarse polishing (85  $\mu\text{m}$  SiC) resulting in dense clumps of fibers while smoother polishing (1  $\mu\text{m}$  alumina) results in scattered, individual fibers. Fiber growth is suspected to be nucleated at defect sites on the electrode surface.

The fibers lack any discernible long range crystalline order, as seen by selected area electron diffraction and powder X-ray diffraction.

X-ray photoelectron spectroscopic measurements for samples prepared in acetonitrile solution indicate that the fibers consist primarily of carbon, although significant quantities (5-10%, calculated using the relative peak areas and previously determined sensitivity factors) of Cl, O, and N are also present.

Infrared (IR) spectra of the material feature a peak at 2210  $\text{cm}^{-1}$  which implies acetylene or  $\text{C}\equiv\text{N}$  groups. Incorporation of a  $\text{C}\equiv\text{N}$  species could result from acetonitrile encapsulation; however a peak at 2150  $\text{cm}^{-1}$  was also seen from samples prepared in methylene chloride, implying the existence of  $\text{C}\equiv\text{C}$  species. The aliphatic C-H stretches in the IR at 2881 and 2967  $\text{cm}^{-1}$ , and C-H bending modes at 1460 and 1387  $\text{cm}^{-1}$  arise from intercalated tetrabutylammonium ions.

Cyclic voltammetry experiments show reversible ion exchange can take place as the potential is scanned. Figure 2 shows the IR spectrum of a fiber sample doped initially with tetrabutylammonium ions. As the potential is swept between 0.0 volts and -0.62 volts vs. Ag/AgCl in acetonitrile containing 0.1M PPNCl, the tetrabutylammonium ion is exchanged with the bis-(triphenylphosphoranylidene) ammonium ion. After cycling, a second IR spectrum, also shown in Figure 2, shows that tetrabutylammonium ions have been partially replaced.

Heat treatment of the fibers at temperatures up to 500°C show the disappearance of aliphatic CH groups, as measured by infrared spectroscopy. X-ray diffraction experiments show the fibers remain amorphous after heating to these temperatures.

## References

- 1 K. Kinoshita. *Carbon: Electrochemical and Physicochemical Properties*. Wiley, New York (1988).
- 2 H. Nishihara, H. Harada, S. Kaneko, M. Tateishi and K. Aramaki, *J. Chem. Soc., Chem. Comm* 26-27 (1990).
- 3 H. Nishihara, H. Harada, M. Tateishi, K. Ohashi and K. Aramaki, *J. Chem. Soc. Farad. Trans.* 87, 1187-1192 (1991).
- 4 H. Nishihara, K. Ohashi, S. Kaneko, F. Tanaka and K. Aramaki, *Synth. Met.* 42, 1495-1499 (1991).
- 5 L. Kavan, in *Chemistry and Physics of Carbon*, eds. Thrower, P.A., pp. 69-171, Marcel Dekker, New York (1991).
- 6 D. F. Shriver and M. A. Drezdson. *The Manipulation of Air-Sensitive Compounds*, pp. 91-92, John Wiley and Sons, Inc., New York (1986).

Dist	Special
A-1	20




Figure 1: SEM micrograph of electro-deposited carbonaceous fibers. Bar at lower right represents 12 microns.




Figure 2: Infrared spectra before (top) and after (bottom) cyclic voltammetry experiments, showing cation replacement.